

RICHELIEU HARDWARE LTD.

7900 Henri-Bourassa Ouest
St-Laurent, Quebec-QC, H4S 1V4 (CANADA)
☎ +1 450 664 0163 www.richelieu.com
E-mail: info@richelieu.com

Retarder

Reference: **DU5023L**

Product description

Thinner for the preparation for use of nitrocellulose, pre-catalysed and post-catalysed varnishes and lacquers.

Physical-chemical characteristics

Density: 0,890 g/cm³ ±0.010
Flash point: 19 °C
General properties: Slow evaporation.

Application systems

Thinner valid to adjust the viscosity of application of finishing coatings.

Usage field

Thinner used as retarder to prepare for use of clear and pigmented coatings.
It has to be employed in general when the room temperature exceeds 28-30°C. It can be employed at lower temperatures too when problems such as air insertion or bubbles appear inside the wet film.

Storing and packaging.

Store the container perfectly closed, in a dry place, fresh and well ventilated and keep product away from sun light, heat and ignition focus, electrical sources and incompatible materials.

- Maximum time of stock: Unlimited stability as long as the container remains without open.
- Available sizes: 25 litres.

Observations

Follow the instructions on the package label and take care of precautions for storing and handling, according to those indicated on the Safety Data Sheet.